

DENSO BUTYL MASTIC TAPE

Double-Sided Butyl Adhesive Tape

Description

Denso Butyl Mastic Tape is a 100% solids, non-hardening, thick butyl based sealant tape. It has an aggressive surface tack and high tensile strength. These properties provide an immediate bond, without the need of a primer. Available in black rolls on easily removable release paper.

Uses

Denso Butyl Mastic Tape is ideal for the joining and sealing together of a variety of other surfaces including polyethylene, polypropylene, PVC, concrete, metal, wood and cadwelds.

Features

- Easy to apply by hand
- Easy to remove release paper
- No primer is required
- Wide application temperature
- Aggressive grip
- Stays flexible
- Excellent conformability and consistent uniform thickness
- Non-shrinking and non-corrosive
- Double sided adhesive

Application

Prepare surfaces by removing dust, dirt, grease, etc. No primer is needed. Peel off release paper and apply tape to surface.



Denso Butyl Mastic Tape

Property Specifications

PROPERTIES	ENGLISH
% Solid	100%
Elongation at Break (ASTM C908)	300%
Water Resistance	Excellent
Sag Resistance	None
Tensile Strength (ASTM C907)	10-18 PSI
Lap Shear Strength (ASTM C961)	6 PLI minimum
Low Temperature Flexibility (ASTM C765)	Pass @ 0°F
Temperature Range	
For Application	0°F to 120°F
For Continuous Service	-25°F to 180°F
Dimensions	
Roll Length	2" x 30'
Thickness (standard)	1/8"
Color	Black

Packaging

Roll Width	Roll Length	Rolls*/ Case
in.	ft.	ea.
2"	30'	12

Other roll widths are available on request.

STORAGE: Keep in cool dry place. Denso Butyl Mastic Tape has a 2 year shelf life from date of manufacture when stored at or below 80°F (27°C).



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.