

# DENSO MB-50 TAPE

## All Purpose Polyolefin Fabric/Bitumen Pipeline Tape

### Description

Denso MB-50 Tape is a tough, dimensionally stable, woven polyolefin fabric backing, laminated to a thick layer of polymer modified bitumen pressure sensitive adhesive.

### Uses

For the anti-corrosion protection of buried or immersed pipes and fittings. The tapes can be applied by hand or machine to weld joints, bends, bare pipe lengths and pipe fittings.

### Features

- Applied to marginally prepared surfaces (SSPC SP 2-3)
- Cold applied
- Good conformability
- Good impact resistance
- Excellent adhesion to pipe and self
- Excellent resistance to cathodic disbonding
- Compatible with common pipe coatings

### Application

Prepare surfaces by removing all loose scale, rust or other foreign matter by grit blasting or wire brush. Surface must be clean, dry and free of grease. Apply thin film of Denso Primer D to all surfaces to be wrapped and allow to dry. Peel back interleaving and apply adhesive side of the tape to the primed surface and press down. Apply the tape spirally with enough tension to make it conform. Remove interleaving as wrapping proceeds. Overlap each turn by at least 1" or 55% to achieve double thickness.

Irregular surfaces such as valves, flanges, etc. may require the use of Denso Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



# Denso MB-50 Tape

## Property Specifications

PROPERTIES	ENGLISH	METRIC
<b>Thickness</b> (ASTM D1000)		
Backing	25 mils	0.65 mm
Adhesive	25 mils	0.65 mm
Total	50 mils	1.30 mm
<b>Weight</b>	0.25 lbs/ft <sup>2</sup>	1.2 kg/m <sup>2</sup>
<b>Breaking Strength</b> (ASTM 1000)	28.5 lbf/in.	5 N/mm
<b>Tear Strength</b> (ASTM 1004)	5.39 lbf	24 N
<b>Grab Tensile Strength</b> (Warp)	143 lbf	650 N
<b>Trapezoidal Tear Strength</b> (Warp)	88.3 lbf	400 N
<b>Elongation</b>		
Warp	19%	19%
Weft	15%	15%
<b>Adhesion Peel Strength</b> (ASTM D1000)		
To Primed Steel	15.4 lbf/in.	2.7 N/mm
To Self	15.4 lbf/in.	2.7 N/mm
<b>Impact Strength</b> (ASTM G-14)	3.68 ft lb	5 Nm
<b>Dielectric Strength</b>	20 Kv	20 Kv
<b>Maximum Service Temperature</b>	158°F	70°C
<b>Recommended Holiday Test Voltage</b>		
Single Layer	10 Kv	10 Kv
Double Layer	15 Kv	15 Kv

## Quantity Estimates

Tape Width	Tape Length	Rolls/ Case	Coverage with 1" Overlap	Coverage with 50% Overlap
in.	ft.	ea.	ea.	ea.
2"	50'	12	45 ft <sup>2</sup> /case	45 ft <sup>2</sup> /case
4"	50'	6	75 ft <sup>2</sup> /case	45 ft <sup>2</sup> /case
6"	50'	4	84 ft <sup>2</sup> /case	45 ft <sup>2</sup> /case



### DENSO NORTH AMERICA

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

*A Member of Winn & Coales International*

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.