

DENSO BITUMEN MASTIC

Single Component Bitumen Mastic Coating

Description

Denso Bitumen Mastic is a high build single component cold applied liquid bituminous coating.

Uses

Corrosion protection on buried pipe, flanges, valves and underground storage tanks.

Features

- Single component
- High build
- Can be applied with brush or roller
- Self-Priming
- VOC compliant
- Does not shield cathodic protection

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSC-SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 to 7,000 psi is also suitable. In severely corrosive environments SSPC-SP6 commercial blast cleaning should be used. The product should be mixed thoroughly prior to application. For brush application a soft bristle brush is recommended.



Denso Bitumen Mastic

TECHNICAL DATA

PROPERTIES	VALUE
Application Temperature	50°F to 120°F (10°C to 49°C)
Solids by Weight	63%
Thickness	
Wet Film Thickness (WFT)	30 mils min.
Dry Film Thickness (DFT)	20 mils min.
Theoretical Coverage	
20 mils (DFT)	52 ft ² /gallon
30 mils (DFT)	39 ft ² /gallon
40 mils (DFT)	26 ft ² /gallon
Mix Ratio	Single Package
Flash Point	100°F (38°C)
Drying Time	Touch Dry Backfill Time
20 mils	2 hours 24 hours
30 mils	2 hours 24 hours
40 mils	2 hours 24 hours
Resistance to Salts & Alkalies	Excellent
Resistance to Water	Excellent
Resistance to Oils, Greases & Solvents	Poor
Service Temperature	-60°F to 325°F (-51°C to 163°C)

STORAGE: Maximum 18 months when stored in original containers between 40°F to 80°F (4°C to 27°C).

CLEANING: Clean equipment with MEK or equivalent solvent cleaner.

HEALTH AND SAFETY: Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheets for further information.

PACKAGING: 4 ea. 1 gallon containers
5 gallon containers



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.