

# DENSO OUTERARMOUR

## Liquid Epoxy Topcoat for Denso Petrolatum Tapes

### Description

Denso OuterArmour is a two-component 100% solids liquid epoxy coating. It is a tough/durable topcoat that provides excellent abrasion resistance for Denso Petrolatum Tapes.

### Uses

- Mechanically protects Denso Petrolatum Tapes
- Flexible and durable
- Can be brush, roller or Denso applicator pad applied
- Provides excellent resistance to water, acids, alkalis, salts and mild solvents
- Can be applied in one coat up to 40 mils

### Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi is also suitable. Apply a thin film of Denso Paste, which serves as a primer. Spirally wrap the tape with a minimum 1" overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams.

Mix each of the base and hardener to an even consistency. Pour Part B (Hardener) into Part A (Base) and mix until an even color is achieved making sure all sides of container are scraped. Immediately begin applying mixed material onto surface with brush, roller or Denso applicator pad. Special attention shall be taken to ensure that there are no pin holes or low film thickness areas. A second coat may be necessary.



# Denso OuterArmour

## TECHNICAL DATA

PROPERTIES	VALUE
Solids By Weight	100%
Color	Gray
Components	Two
Gloss	Semi-Gloss
Mixing Ratio (By Vol.)	1 to 1
Weight/Gallon (Mixed)	11.8 lbs.
Pot Life @ 77°F (100 Grams)	30 minutes
Theor. Coverage @ 40 mils	40 sq. ft./gal.
Recommended Dry Film Thickness	Min. 20 mils
Application Temperature	Min. 50°F (10°C)
Service Temperature	-30°F (-34°C) to 158°F (70°C)
Dry Time @ 77°F:	
To Touch	2 hours
To Handle	4 hours
To Recoat	2 to 4 hours

**STORAGE:** Store in a dry, well ventilated area. Shelf life 2 years.

**HEALTH & SAFETY:** Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheet.

**PACKAGING:** Supplied in 1.5 liter kits. Other size available on request.

The Denso logo consists of the word "Denso" in a bold, sans-serif font, enclosed within a rectangular border. A registered trademark symbol (®) is located at the top right of the border.

**DENSO NORTH AMERICA**

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

***A Member of Winn & Coales International***

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.