

# DENSO COLORTAPE

## Primer-Integrated Color Petrolatum Tape

### Description

Denso ColorTape is composed of a non-woven synthetic fabric carrier, fully impregnated with a stable pigmented petrolatum compound. Available in grey (other colors available upon special order).

### Uses

Denso ColorTape is designed to withstand extreme temperature variations. Provides long term corrosion protection to wet or dry pipes, flanges, valves and related surfaces. It is specially stabilized and pigmented for use above ground where appearance is important.

### Features

- Does not require a primer
- Applied to marginally prepared surfaces (SSPC SP 2-3)
- UV resistant
- Conforms to irregular shapes and profiles
- Can be applied to cold, wet surfaces
- Not effected by water, acid, salts or soil organics
- Encapsulation of lead paint
- Contains no solvents
- Easy application from arctic to tropical temperatures
- Ready for immediate service after application
- Meets AWWA C217 Standard
- Can be used above and below ground

### Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. Spirally wrap the tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



# Denso ColorTape

## PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
<b>Thickness</b> (ASTM D1000)	48 mils	1.2 mm avg.
<b>Weight</b>	.255 lbs/ft <sup>2</sup> .	1.25 kg/m <sup>2</sup> avg.
<b>Breaking Strength</b> (ASTM 1000)	22.5 lbf/in.	200 N/50 mm min.
<b>Water Vapor Transmission</b> (ASTM E96 - 66 Procedure A)	0.006 perms avg.	0.006 perms avg.
<b>Elongation @ Break</b>	10% avg.	10% avg.
<b>Breakdown Voltage</b> (55% overlap)	16 kV min.	16 kV min.
<b>Resistance to Cathodic Disbonding</b> (ASTM G-8 - 30 days)	.28 in <sup>2</sup> avg.	180 mm <sup>2</sup> avg.
<b>Resistance to Acids, Alkalies and Salts</b>	Excellent	Excellent
<b>Maximum Service Temperature</b>	140°F	60°C
<b>Roll Widths</b>	2" to 12"	50 to 300 mm
<b>Roll Length</b>	25 ft	7.5 m
<b>Color</b>	Gray	Gray

## Quantity Estimates

Tape Width	Rolls*/ Case	Coverage with 1" Overlap	Coverage with 55% Overlap
in.	ea.	ea.	ea.
2"	24	45 ft <sup>2</sup> /case (4.18 m <sup>2</sup> )	45 ft <sup>2</sup> /case (4.18 m <sup>2</sup> )
4"	12	74 ft <sup>2</sup> /case (6.88 m <sup>2</sup> )	45 ft <sup>2</sup> /case (4.18 m <sup>2</sup> )
6"	8	83 ft <sup>2</sup> /case (7.71 m <sup>2</sup> )	45 ft <sup>2</sup> /case (4.18 m <sup>2</sup> )
8"	8	116 ft <sup>2</sup> /case (10.78 m <sup>2</sup> )	60 ft <sup>2</sup> /case (5.57 m <sup>2</sup> )
12"	4	91 ft <sup>2</sup> /case (8.45 m <sup>2</sup> )	45 ft <sup>2</sup> /case (4.18 m <sup>2</sup> )

\*All rolls are 25 feet (7.6 meters) in length.



### DENSO NORTH AMERICA

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

**A Member of Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.