

DENSYL KF TAPE

Petrolatum Tape with Fire Retardants

Description

Densyl KF Tape is composed of a non-woven synthetic fabric carrier, fully impregnated with a neutral compound based on saturated petrolatum and inert siliceous fillers and non-toxic fire retardant additives.

Uses

Densyl KF Tape are designed to withstand extreme temperature variations. The tapes provide long term corrosion protection to pipes, flanges, valves and related surfaces.

Features

- Applied to marginally prepared surfaces (SSPC SP 2-3)
- Conforms to irregular shapes and profiles
- UV resistant
- Can be applied to cold, wet surfaces
- Not effected by water, acid, salts or soil organics
- Encapsulation of lead paint
- Contains no solvents
- Easy application from arctic to tropical temperatures
- Ready for immediate service after application
- Meets AWWA C217 Standard
- Over a eighty year history of proven applications
- Can be applied above and below ground
- Contains fire retardant additives

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. Apply a thin film of Denso Paste, which serves as a primer. Spirally wrap the tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. For additional mechanical protection, an overwrap may be used to increase impact strength and electrical resistance.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



Densyl KF Tape

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Thickness (ASTM D1000)	.46 mils	1.15mm avg.
Weight	.295 lbs/ft ² .	1.44 kg/m ² avg.
Breaking Strength (ASTM 1000)	22.5 lbf/in.	200 N/50mm min.
Elongation @ Break	10% avg.	10% avg.
Breakdown Voltage (55% overlap)	16 kV min.	16kV min.
Resistance to Cathodic Disbonding (ASTM G-8 - 30 days)	<0.78 in ² avg.	<500mm ² avg.
Resistance to Acids, Alkalies and Salts	Excellent	Excellent
Fire Resistance - Surface Spread of Flame BS 476: Part 7:1971	Clas 2	Class 2
Temperature Range		
For Application	41°F to 131°F	5°C to 55°C
For Service	-4°F to 158°F	-20°C to 70°C
Roll Length	33 ft. min.	10 m. min.
Roll Widths	2" to 12"	50 to 300 mm
Recommended Primer	Denso Paste Denso Paste S105 or Denso Hi-Tack Primer	

Quantity Estimates

Tape Width	Rolls*/ Case	Coverage with 1" Overlap	Coverage with 55% Overlap
in.	ea.	ea.	ea.
2"	36	87 ft ² /case (8.08 m ²)	87 ft ² /case (8.08 m ²)
4"	18	145 ft ² /case (13.47 m ²)	87 ft ² /case (8.08 m ²)
6"	12	162 ft ² /case (15.05 m ²)	87 ft ² /case (8.08 m ²)
8"	8	150 ft ² /case (13.94 m ²)	77 ft ² /case (7.15m ²)
12"	6	177 ft ² /case (16.44 m ²)	87 ft ² /case (8.08 m ²)

*All rolls are 33 feet (10 meters) in length.



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.