

DENSO PASTE HT

High Temperature Paste/Primer

Description

Denso Paste HT is a soft brown petrolatum paste containing moisture displacing corrosion inhibiting compounds for application by stiff brush or gloved hand. It does not dry, harden or crack.

Uses

Primarily used as a paste/primer to protect steel surfaces. Denso Paste HT will penetrate existing rust, displacing moisture and pacify the surface. Rust and corrosion protection is controlled as water, oxygen and other corrosioeve materials cannot penetrate the gel structure of the paste. It is also used as a temporary coating for exposed metal.

Features

- Superior performance up to 375°F (190°C)
- Highly resistant to bleeding or seperation
- Minimal surface preparation (SSPC SP 2-3)
- Can be applied in any climate
- Can be applied to wet surfaces
- Contains no V.O.C.'s
- Can be applied by inexperienced personel
- No shut downs necessary
- Meets AWWA C-217

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. Apply a thin uniform coat of Denso Paste HT to the entire surface with a gloved hand, brush or rag.



Denso Paste HT

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Solids Content	>98%	>98%
Specific Gravity	1.08	1.08
Specific Volume	26 cu in/lb.	925 cc/kg
Flash Point	>550°F	>288°C
Maximum Service Temperature	375°F	191°C

COVERAGE:

484 ft² per case
(45.06 m² per case)

PACKAGING:

4 each 5.5 lb tubs per case
(4 each 2.5 kg tubs per case)



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.