

DENSO PRIMING SOLUTION

Spray Applied Petrolatum Tape Primer

Description

Denso Priming Solution is a petrolatum primer in aromatic hydrocarbon solvent. The primer can be applied by brush or spray prior to the application of petrolatum tapes and compounds.

Uses

The primer is typically used for large areas to provide a faster application. Denso Priming Solution will penetrate existing rust, displace moisture and aid the adhesion of petrolatum tapes.

Features

- Minimal surface preparation (SSPC SP 2-3)
- Can be applied in any climate
- Can be applied to damp surfaces
- No shut down necessary
- Can be applied by inexperienced personnel
- Unaffected by water, acids and salts
- Brush or spray applied

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi is also suitable. Apply a thin uniform coat of Denso Priming Solution by brush. For spray applications, use a 45:1 pump equipped with a large tip.



Denso Priming Solution

Property Specifications

PROPERTIES	ENGLISH	METRIC
Specific Gravity	0.89	<i>0.89</i>
Dry Film Thickness	2 mils	<i>50 micron</i>
Flash Point	90°F min.	<i>32° C min.</i>
Maximum Service Temperature	158°F	<i>70° C</i>
Coverage Capacity	484 ft ² /1.3 gallon	<i>45 m²/5 liters</i>
Packaging	4 each 1.3 gallon containers per case	<i>4 each 5 liter containers per case</i>

COVERAGE:

1,936 ft² per case
(180 m² per case)

PACKAGING:

4 each 1.3 gallon containers per case
(4 each 5 liter containers per case)



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.