

# **DENSO FIBER-WRAP**

**Fiberglass Fabric Outerwrap Used Over Petrolatum Tape Systems**

## **Description**

Denso Fiber-Wrap is a resin coated, woven fiber-mesh fabric that is .005 inches (127 microns) in thickness and exhibits excellent tensile strength.

## **Uses**

Used as an outerwrap for Denso Petrolatum Tape Systems for straight pipe. Provides additional protection against backfill and soil stress.

## **Features**

- Excellent tensile strength
- Superior holding force
- Provides protection against backfill
- Provides protection against soil stresses

## **Application**

The Denso Fiber-Wrap shall be spirally wrapped using sufficient tension to wrap over the Denso Petrolatum Tape. Apply using a minimum 1" (25 mm) overlap while pressing firmly onto the Denso Petrolatum Tape.



# Denso Fiber-Wrap

## Property Specifications

PROPERTIES	VALUES
Tensile Strength (per 1 inch /25 mm width)	85 lb. min. (38.25 kg)
Thread Count per Inch:	
Warp Threads	20
Fill Threads	10
Thickness	.005 inches (127 microns)
Color	White
Roll Width	4", 6", and 12" (10 mm, 150 mm, and 300 mm)
Roll Length	150 ft (45 m)

## Quantity Estimates

Tape Width	Rolls*/ Case	Coverage with 1" (25 mm) Overlap	Coverage with 50% Overlap
4" (100 mm)	6	225 ft <sup>2</sup> /case (21 m <sup>2</sup> /case)	150 ft <sup>2</sup> /case (14 m <sup>2</sup> /case)
6" (150 mm)	4	250 ft <sup>2</sup> /case (23 m <sup>2</sup> /case)	150 ft <sup>2</sup> /case (14 m <sup>2</sup> /case)
12" (200 mm)	2	825 ft <sup>2</sup> /case (77 m <sup>2</sup> /case)	150 ft <sup>2</sup> /case (14 m <sup>2</sup> /case)

\* All rolls are 150 feet (45 m) in length.



**DENSO NORTH AMERICA**

**HOUSTON:**

9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**

90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

**A Member of Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.