

# DENSO GLASS OUTERWRAP 70

## Protective Fiberglass Outerwrap

### Description

Denso Glass Outerwrap 70 is a fiberglass cloth impregnated with a water activated resin that is used as a protective outer wrap over Denso Marine Piling Tape. Available in brown (other colors available upon special order).

### Uses

A protective coating which offers exceptional mechanical and impact strength for underwater, underground, and above ground pipes and piles.

### Features

- Resists cold and hot temperatures
- Easy to apply, no mixing or messy clean up
- Resistant to water, acid, salts, or soil organics
- Can be applied underwater or to wet surfaces
- Minimal surface preparation required
- Quick, long term protective coating, ready for immediate service
- Contains no solvents
- Can be top coated for aesthetics

### Application

Remove all dirt, loose paint, spalling concrete, rotted wood, marine growth and other contaminants by abrasive blasting or high pressure water blasting. Hand or power tool cleaning methods may be used but are of limited benefit and are time consuming. Spirally wrap a layer of Denso Marine Piling Tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. Using rubber gloves, remove the Denso Glass Outerwrap 70 from the hermetically sealed foiled pouch and soak in temperate water (salt or fresh) for 20 to 30 seconds. Remove and begin wrapping tightly, overlapping a recommended 50%.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.

For more information, please refer to the SeaShield Series 70 Engineering Specification.



# Denso Glass Outerwrap 70

## PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Thickness	11 mils avg.	0.28 mm
Flexural Strength (ASTM D709-71)	16,100 psi	113,200 Kgs/mm <sup>2</sup>
Tensile Strength (ASTM D638)	24,900 psi	175,071 Kgs/mm <sup>2</sup>
Compression Strength (ASTM D695-77)	26,600 psi	187,024 Kgs/mm <sup>2</sup>
Dielectric Strength	16,060 volts	16,060 volts
Maximum Service Temperature	350°F	177°C
Application Temperature	32°F to 150°F	(-18°C to 65°C)
Setting Time		
@ 70°F (21°C)	30 minutes	30 minutes
@ 90°F (32°C)	15 minutes	15 minutes
Color	Brown	Brown

## Quantity Estimates

Tape Width	Roll Length	Rolls*/ Case	Coverage with 50% Overlap
in.	ea.	ea.	ea.
3" (75 mm)	9' (2.7 m)	15	17 ft <sup>2</sup> /case (1.6 m <sup>2</sup> /case)
4" (100 mm)	30' (9 m)	5	25 ft <sup>2</sup> /case (2.3 m <sup>2</sup> /case)
8" (200 mm)	40' (12 m)	3	40 ft <sup>2</sup> /case (3.7 m <sup>2</sup> /case)

\*Other widths and lengths available upon special request.

**SHELF LIFE:** 24 months.



**DENSO NORTH AMERICA**

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

**A Member of Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.