

PRODUCT DATA SHEET

DENSO GLASS OUTERWRAP UV

UV Protective Fiberglass Outerwrap

Description

Denso Glass Outerwrap UV is a fiberglass cloth impregnated with a water activated aliphatic polyurethane resin that is used as a protective outer wrap over Denso Petrolatum Tape.

Uses

A protective coating which offers exceptional mechanical and impact strength for underwater, underground, and above ground pipe and piles. The aliphatic polyurethane provides UV stability.

Features

- Resists cold and hot temperatures
- Easy to apply, no mixing or messy clean up
- Resistant to water, acid, salts, or soil organics
- Can be applied underwater or to wet surfaces
- Minimal surface preparation required
- Quick, long term protective coating, ready for immediate service
- Contains no solvents
- Can be top coated for aesthetics
- UV Resistant

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. Spirally wrap a layer of Denso Petrolatum Tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. Using rubber gloves, remove the Denso Glass Outerwrap UV from the hermetically sealed foiled pouch and soak in temperate water (salt or fresh) for 20 to 30 seconds. Remove and begin wrapping tightly, overlapping a recommended 50%.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



Denso Glass Outerwrap UV

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Flexural Strength (ASTM D709-71)	16,100 psi	113,200 Kgs/mm ²
Tensile Strength (ASTM D638)	24,900 psi	175,071 Kgs/mm ²
Compression Strength (ASTM D695-77)	26,600 psi	187,024 Kgs/mm ²
Dielectric Strength	16,060 volts	16,060 volts
Maximum Service Temperature	350°F	177°C
Setting Time		
@ 70°F (21°C)	2.5 hours	2.5 hours
@ 90°F (32°C)	1 hour	1 hour
Color	Grey	Grey

Quantity Estimates

Tape Width	Roll Length	Rolls*/ Case	Coverage with 50% Overlap
in.	ea.	ea.	ea.
3" (75 mm)	9' (2.7 m)	15	17 ft ² /case (1.6 m ² /case)
4" (100 mm)	30' (9 m)	5	25 ft ² /case (2.3 m ² /case)
8" (200 mm)	40' (12 m)	3	40 ft ² /case (3.7 m ² /case)

*Other widths and lengths available upon special request.

SHELF LIFE: 6 months.



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.