

# **DENSO PAVING TAPE**

## **Cold Applied Joint Sealing Compound**

### **Description**

Denso Paving Tape is a cold applied, synthetic fabric reinforced tape with a high tack bituminous adhesive. It incorporates a disposable release liner and is produced in roll form. It is used in conjunction with Denso Primer D.

### **Uses**

Denso Paving Tape is used for surface sealing of open cracks and seams up to 0.20" (5 mm) width in asphalt and concrete pavements, prior to overlay with new asphalt.

### **Features**

- Cold applied installation
- Fast application
- Instant seal against water
- Prevents cracking in asphalt overlay
- Effective on asphalt and concrete

### **Application**

Clean and dry the crack area. Apply Denso Primer D to the crack area to the width of the tape selected. Allow the primer to dry to a tack consistency. Apply the paving tape, following the line of the crack. At abrupt change in direction, cut the tape and start a new section, overlapping onto the previous tape. The release liner is removed prior to filling with new asphalt.



# Denso Paving Tape

## Property Specifications

<b>PROPERTIES</b>	<b>English</b>	<b>Metric</b>
<b>Thickness</b>	63 mils	1.6 mm
<b>Widths</b>	4", 6"	100 mm, 150 mm
<b>Roll Length</b>	40'	12 Meters
<b>Breaking Strength</b>	40 lbf/in.	7 N/mm
<b>Tear Strength (ASTM D1004)</b>	5.6 lbf	25 N average
<b>Application Temperature</b>	46 to 113°F	8 to 45°C
<b>Packaging</b>	8 (100mm), 4 (150mm) rolls per case	
<b>Denso Primer D:</b>		
Drying Time	10 minutes	10 minutes
Flash Point	73°F	23°C
Coverage	0.26 Gal/492'	1 Liter/150 Meters
Packaging	1.3 Gallons	5 Liter can



### DENSO NORTH AMERICA

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

**A Member of Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.