

SeaShield Marine Systems

SeaShield 530 Injectable Epoxy

Low Exotherm Epoxy Injection Resin

SeaShield 530 is a modified 2-component epoxy for larger cracks/voids and is formulated to produce low exotherm and structural stability in such applications.

Uses

SeaShield 530 Injectable Epoxy is designed for application using a pressure pot or other single component pumps. It has a relatively long pot life. Because of its lower heat of exotherm, it can be used to fill larger voids and where necessary also provides excellent water displacement, even on underwater injection projects.

Physical Properties

(unmixed) @ 77°F

Component "A" (resin):

Specific Gravity	1.69
Viscosity	2000 cps
Color	White

Component "B" (hardener):

Specific Gravity	0.96
Viscosity	100 cps
Color	Black

Physical Properties

(mixed) @ 77°F

Specific Gravity	1.62
Viscosity	1200 cps
Color	Gray
Solids by weight	100%

Mixing Ratios

		Wt.	Vol.
Base	"A"	91	84
Hardener	"B"	9	16

Cure Schedule

Pot Life 200 g. @ 77°F	150 Minutes
Tack-free time @ 50°F/77°F	22/11 Hours
Through cure @ 50°F/77°F	66/33 Hours

Cure time is considerably longer at colder temperatures.

Peak Exotherm vs. Typical Epoxy Injection Resin

Cylinder (2.5" x 3" HT)

SeaShield 530	91°F (-33°C)
Typical Epoxy	91°F (-33°C)

Box (6" x 12" x 3")

SeaShield 530	163°F in 140 mins.
---------------	--------------------

Box (6" x 6" x 3")

SeaShield 530	378°F in 60 mins.
---------------	-------------------

Pot Life (Pressure Pot) @ 77°F

SeaShield 530, 1 Gallon Sample:	
Practical working time:	45 mins.

Minimum Application Temperature

SeaShield 530 Injection Epoxy cures at temperatures down to 32°F.

Moisture Sensitivity

SeaShield 530 Injection Epoxy has excellent damp adhesion and water displacement capabilities.

Physical Testing (.20 cubes)

Compressive Strength	7 Days	28 Days
Dry	77.9	97.5 MPa
Tremmied Under Water	77.5	97.5 MPa

Slant/Shear Adhesion

ASTM C881/C882 exceeds requirements of this specification on wet surfaces at 41°F (5°C).

Surface Preparation

The area adjacent to the crack must be cleaned to obtain good adhesion. SeaShield 525 Epoxy is used to seal the crack and the injection devices. These devices may be plastic tees or ports depending on the technique used. To use ports (spaced every 6" to 12"), it is necessary to use a vacuum drill to make the holes for the injection ports. The placing of the injection devices is critical. Foreign material in a crack may be a major factor in the success of injection. It is sometimes possible to flush cracks to remove contaminants. A thorough study in this regard is always necessary.

Mixing and Application

SeaShield 530 Injectable Epoxy is designed for use with a pressure pot or other single component pump.

1. After the crack has been prepared for the pressure injection process, resin is pumped from one port (or tee) to the next in sequence. On a vertical crack, one starts at the bottom. If there is water in the crack it must be expelled by the resin being injected and this phase must continue until clear, water-free resin is emerging from the next port (or tee).
2. The injection process must be continuous until the entire crack is filled with resin.
3. Test samples of the resin being injected must be taken before, during and after the injection is complete. It is imperative that the injection process be continually monitored to ensure that the resin injected is properly mixed and will cure satisfactorily.

Note: When using a pressure pot, pour contents of "B" into "A" and mix well with a low speed power mixer (200 - 300 rpm) until one even color develops. Pour this into pressure pot.

Clean Up

Use MEK Solvent. CAUTION - This solvent is flammable so there must be no open lights, flames, sparking motors or pilot lights in the vicinity. All equipment must be cleaned immediately after use.

Safety and Toxicity

Epoxy systems are capable of producing severe injury to, or destruction of, skin and eye tissues. They are classified as corrosive for shipping purposes. Precautions must be taken to prevent prolonged or repeated skin contact and it is essential to protect the eyes from splashes. Protective clothing, rubber gloves and chemical goggles should be worn when working with these products.

Some people become sensitized when working with epoxy resin systems. The sensitization may appear in the form of skin or respiratory reactions. Avoid breathing vapors, particularly if these products are used in a confined area. Face mask with respirator #1224 is usually adequate. Air supplied mask is suitable for use in confined areas.

Storage

Store in heated area and on pallets. Do not allow products to freeze. Shelf life in unopened containers is two years.

Packaging

1 Gallon Units (A & B)

Each container is clearly marked with product name, component designation ("A" or "B"), manufacturer's name, batch number and ratio of component mixtures. Containers of "A" and "B" are color coded the same.

Warranty

Manufacturer WARRANTS that the product conforms to its chemical description and is reasonably fit for the purpose stated on its Technical Bulletin when used in accordance with its directions. Manufacturer makes NO OTHER WARRANTY either expressed or implied. Buyer assumes all risk in handling.



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International