

DENSO HI-TACK PRIMER

Hi-Tack Petrolatum Tape Primer

Description

Denso Hi-Tack Primer is a high melting point petrolatum with added adhesive properties. The primer is very tacky and aids adhesion of petrolatum tapes

Uses

The primer is typically used on irregularly shaped surfaces or where additional adhesive qualities are required. Denso Hi-Tack Primer will penetrate existing rust, displace moisture and aid the adhesion of petrolatum tapes.

Features

- Minimal surface preparation (SSPC SP 2-3)
- No shut down necessary
- Can be applied by inexperienced personnel
- Unaffected by water, acids and salts
- Conforms to irregular surfaces
- Hand, brush or spray applied

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. Apply a thin uniform coat of Denso Hi-Tack Primer by hand or brush. Spray application using a 45:1 pump with large tip may be suitable for large areas.



Denso Hi-Tack Primer

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Specific Gravity	.91	.91
Flash Point	90°F min.	32°C min.
Maximum Service Temperature	149°F	65°C
Coverage Capacity	269 ft ² /1.3 gallon	25 m ² /5 liters
Packaging	4 each 1.3 gallon containers per case	4 each 5 liter containers per case

COVERAGE:

1,076 ft² per case
(100 m² per case)

PACKAGING:

4 each 1.3 gallon containers per case
(4 each 5 liter containers per case)



DENSO NORTH AMERICA

HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.