

LEADERS IN CORROSION PREVENTION AND SEALING TECHNOLOGY

OVER 130 YEARS SERVICE TO INDUSTRY



# **Densoband Primer**

Fast drying bitumen based primer

## Composition

Densoband Primer consists of oxidised bitumen in aromatic hydrocarbon solvent.

#### Uses

Densoband Primer is used for all surfaces prior to the application of Densoband, Denso Overbanding Tape and Denso Paving Tape.

### Characteristics

- Easy to apply with brush or roller, and
- Fast drying, less than 15 minutes.

### Application

See Instructions for use for additional details.

Ensure the surface is dry and free from dust and loose material before primer is applied. Application Temperature: 0°C to 55°C.

# Availability

Densoband Primer is available in 5 litre metal containers.

Other sizes may be available on request.

### **Storage Conditions**

Store in a cool and dry place in original packaging.

#### Waste Material

Please do not discard waste material, including packaging, in the surrounding environment. Please follow all relevant legislation for disposal.

## **Typical Properties**

Colour	Black
Specific Gravity	0.94
Solids Content	58% w/w
Flash Point	>23°C
Drying Time	10-15 minutes
Surface Coverage	7-8m²/litre (@ DFT 70 – 80 μm)

Important: Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. FM01548) and an Environmental Management System registered to BS EN 14001 (BSI Certificate 583748).

Winn & Coales (Denso) Ltd Denso House, Chapel Road, London SE27 0TR, United Kingdom



Tel: +44 (0) 20 8670 7511 Fax: +44 (0) 20 8761 2456 Email: mail@denso.net Web: www.denso.net

Page 1 of 1

Revision date: 17/01/2018