

DENSO FB 30 TAPE

Butyl Rubber With Fabric Backing

Description

Denso FB 30 Tape is a butyl rubber adhesive tape with a polyester fabric backing. The tape can be top coated with Denso OuterArmour.

Uses

The tape is used in conjunction with the Denso Tank Base Protection System to seal and protect tank chimes. Can also be used as an outer coating over Denso Petrolatum Tapes or applied direct to steel surfaces.

Features

- Excellent adhesion
- Aggressive Grip
- Good conformability and consistent uniform thickness
- Easily applied with no special equipment
- Compatible with most coatings
- Cold applied
- Stays Flexible
- Easy and fast application
- Fabric backing allows for top coating

Application

For Tank Base Protection System: Prepare surfaces by removing all grease, scale, dirt and rust on the steel and concrete surface. To assure adhesion the surface must be clean, dry and free of grease. Peel back interleaving and apply adhesive side of the tape to the surface and press down. Apply first layer of Denso FB 30 Tape starting at a minimum of 1" (25 mm) below the Denso Hi-Tack Tape and proceed circumferentially around the concrete and tank base. (Note: Denso FB 30 Tape is easier to apply when product is kept between 60F and 90F) If a second layer is required to reach the steel tank base there shall be a minimum of a 1" (25 mm) overlap onto the first layer of Denso FB 30 Tape. Make sure all seams and overlaps are pressed out and adhered. A top coat can be immediately applied after Denso FB 30 Tape is installed.

For Direct to Steel: Prepare surfaces by removing all grease, scale, dirt and rust on the steel and concrete surface. To assure adhesion, the surface must be clean, dry and free of grease. Apply thin film of Denso Butyl Primer to all surfaces to wrapped and allow to dry. Peel back interleaving and apply adhesive side of the tape to the surface and press down. Apply the tape spirally with enough tension to make it conform. Remove interleaving as wrapping proceeds. Overlap each turn by at least 1" or 55% to achieve double thickness. Make sure all overlaps are pressed out and adhered. A top coat can be immediately applied after Denso FB 30 Tape is installed.



Denso FB 30 Tape

Property Specifications

PROPERTIES	VALUE
Adhesive	Modified Butyl
Backing	Polyester
Tensile Strength	790 PSI avg.
Elongation at Break (ASTM D1000)	560% avg.
Dielectrical Strength (ASTM D1000)	20 kV
Water Vapor Transmission (ASTM E398)	< 0.2 g/100 in ² /24 hour
Bonding Time	Immediate
Resistance to Hydrocarbons	Good
Peel Strength	17 lbs per linear inch
Resistance to Acids, Alkalis and Salts	Excellent
Temperature Range	
For Application	35°F to 115°F
For Continuous Service	0°F to 140°F
Dimensions	
Roll Length	50 feet
Width	2", 4", 6"
Thickness (ASTM D1000)	25 mils
Color	White

Quantity Estimates

Tape Width	Rolls*/Case	Coverage with 1" Overlap	Coverage with 50% Overlap
2"	24	100 ft ² /case	100 ft ² /case
4"	12	150 ft ² /case	100 ft ² /case
6"	8	167 ft ² /case	100 ft ² /case

All rolls are 50 feet in length.
Other roll widths are available on request.



DENSO NORTH AMERICA

HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.