

DENSO HOTLINE TAPE

High Temperature Petrolatum Tape

Description

Denso Hotline Tape is composed of a synthetic fabric impregnated with a special blend of high temperature petrolatum, mineral fillers and thermal extenders. It is backed with a thin high density polyethylene film.

Uses

A specifically developed tape for use in high temperature applications. Ideal for pipe work above or below ground, underneath pipe insulation or for pipes laid in concrete.

Features

- Meets NACE RP0375-2006
- Service temperature up to 230°F (110°C) for above ground (180°F / 83°C for below ground)
- Applied to marginally prepared surfaces (SSPC SP 2-3)
- UV resistant
- Resistant to water, acid, salts & soil organics
- Encapsulation of lead paint
- Contains no solvents
- Easy applications from arctic to tropical temperatures
- Ready for immediate service after application
- CSA Z245.30 compliant

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. Spirally wrap the tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. Where tape rolls need to be joined, ensure that the overlap is sufficient between rolls to provide continuous protection. For below ground applications, an approved Denso outerwrap is recommended. *Note: for pipes with operating temperatures below 90°F (32°C), a thin layer of Denso Paste HT may be applied to aid in adhesion.*

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



Denso Hotline Tape

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Thickness (ASTM D1000)	46 mils	1.15 mm avg.
Weight	.295 lbs/ft ² .	1.44 kg/m ² avg.
Breaking Strength (ASTM 1000)	22.5 lbf/in.	200 N/50 mm min.
Elongation @ Break	15% avg.	15% avg.
Breakdown Voltage (55% overlap)	16 kV min.	16 kV min.
Resistance to Cathodic Disbonding (ASTM G-8 - 30 days)	.31 in ² avg.	200 mm ² avg.
Maximum Service Temperature		
Above Ground	230°F	110°C
Below Ground	180°F	83°C
Roll Widths	2" to 12"	50 to 300 mm
Roll Length	33 ft	10 m

Quantity Estimates

Tape Width	Rolls*/ Case	Coverage with 1" Overlap	Coverage with 55% Overlap
in.	ea.	ea.	ea.
2" (50 mm)	36	87 ft ² /case (8.08 m ²)	87 ft ² /case (8.08 m ²)
4" (100 mm)	18	145 ft ² /case (13.47 m ²)	87 ft ² /case (8.08 m ²)
6" (150 mm)	12	162 ft ² /case (15.05 m ²)	87 ft ² /case (8.08 m ²)
8" (200 mm)	8	150 ft ² /case (13.94 m ²)	77 ft ² /case (7.15m ²)
12" (300 mm)	6	177 ft ² /case (16.44 m ²)	87 ft ² /case (8.08 m ²)

*All rolls are 33 feet (10 meters) in length.



DENSO NORTH AMERICA

HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.