### TECHNICAL DATA SHEET

# ARCHCO 15<sup>™</sup>

#### **High Build Flexible Water Based Acrylic Topcoat**

#### **Description**

Archco 15 is a single part, high build, high-performance water-based acrylic topcoat for Denso Tape Systems and the Viscotag™ EZ Wrap Series.

#### Uses

Developed to be used as a topcoat over Denso Petrolatum Tapes, Viscotaq<sup>™</sup> EZ Wrap Series, Denso FB-30<sup>™</sup> Tape, and Denso Glass Outerwrap<sup>™</sup>. Can also be used in conjunction with the Denso Tank Base Protection System as a topcoat for Denso FB 30<sup>™</sup> Tape.

#### **Features**

- Single component
- · Environmentally friendly
- · Can be applied by brush or spray
- Flexible
- Cures at temperatures down to 50°F (10°C)
- Fast dry

## **Application**

Surface to be top coated shall be clean, dry and free of any dust or foreign matter.

**Brush Applications:** Archco 15 can be applied immediately after application of the Denso Tape Systems. Archco 15 shall be applied in two coats consisting of 18 to 23 mils (457 - 584 microns) wet-film thickness per coat. Recoat time is approximately 1 to 2 hours at 77°F (25°C).

**Spray Applications:** An equivalent to a Graco 56:1 airless with 3/8" (9.5 mm) hose with a tip size of 0.031" to .035" (0.8 to 0.9 mm) shall be used. Archco 15 shall be applied in two coats consisting of 18 to 23 mils (457 - 584 microns) wet-film thickness per coat. Recoat time is approximately 1 to 2 hours at 77°F (25°C).



### TECHNICAL DATA SHEET

## Storage

Minimum 2 years when stored in original containers at 50°F (25°C) to 105°F (41°C).

# Cleaning

Clean equipment with soap and water.

# Health & Safety

Wear suitable protective clothing and glasses. See Safety Data Sheets (SDS).

# **Packaging**

5 gallon container (19 liter container).

# Archco 15™

#### TECHNICAL DATA

Properties Value

Solids by Weight 55%

**Weight** 10.71 lbs/gal (1.28 kg/L)

Flash Point 144°F (62°C)

VOC's 0.36 lbs/gal (43 grams/liter)
Viscosity @ 77°F (25°C) Brookfield #6 spindle 10 rpn

Brookfield #6 spindle 10 rpm – 36,500 cP

100 rpm – 6,000 cP

**Recommended Dry Film Thickness**10 to 12 mils (254 - 305 microns) per coat x 2 coats **Recommended Wet Film Thickness**18 to 20 mils (457 - 508 microns) per coat x 2 coats

**Application Temperature** 50°F (25°C) to 130°F (54°C)

**Color** Black or White

Theoretical Coverage 44 SF/Gal @ 20 mils DFT(4 SQM/L @508 microns)



HOUSTON: 9710 Telge Road, Houston, Texas, U.S.A. 77095 Tel: 281-821-3355

Fax: 281-821-0304

TORONTO:

90 Ironside Crescent, Unit 12, Toronto, Ontario, Canada M1X1M3 Tel: 416-291-3435

Fax: 416-291-0898

www.densona.com

info@densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.

VER 2205.20 Page 3 of 3