

ARCHCO 300™ EPOXY PRIMER

Two-Part Epoxy Primer

Description

Archco 300 Epoxy Primer is a low-VOC, two-component coating that provides excellent protection on above-ground steel and concrete surfaces. It's good penetration and adhesive properties ensure excellent protection in long-term exterior exposure. A low-temperature (LT) hardener is available.

Uses

- Offshore Equipment
- Marine Vessels
- Storage Tanks
- Petrochemical Industries
- Oil Production Rigs
- Above Ground Piping
- LT Hardener Available

Features

- Excellent adhesion
- 60-day re-coat window at 70°F (21°C) with any of our linings
- Cures at temperatures down to 35°F (2°C)
- Cures at temperatures down to 25°F (-4°C) when LT hardener is used
- Not susceptible to amine blush
- Excellent wetting properties
- Cures under cool and damp climates
- Good flexibility

Application

APPLICATION CONDITIONS: Surface should be dry, above 35°F (2°C) and at least 5° F (3°C) above the dew point in accordance with SSPC SP-1.

SURFACE PREPARATION: Remove all grease, oil, dirt, dust or other contaminants.

NORMAL SERVICE: SSPC – SP2 and SP3 Hand and Power Tool Cleaning.



TECHNICAL DATA SHEET

CORROSIVE SERVICE: SSPC – SP6 Commercial Blast Cleaning or SSPC – SP10 Near-White Metal Blast Cleaning.

IMMERSION SERVICE: SSPC – SP10 Near-White Metal Blast Cleaning.

CONCRETE SERVICE: Surfaces should be lightly sandblasted and/or acid etched. If acid etching is used, the surface should be rinsed with fresh water and allowed to dry thoroughly before application of the Archco 300 Epoxy Primer.

Note: Concrete must be cured for at least 28 days prior to application of Archco 300 Epoxy Primer.

PREVIOUSLY PAINTED SURFACES: Remove all grease, oil, dirt, dust or other contaminants. Surface must be clean and dry. Remove all rust, rust scale, chalk, and loose peeling paint by SSPC – SP2 or SP3 Hand or Power Tool Cleaning, or SSPC – SP7 Brush-Off Blast Cleaning.

RECOMMENDED TOP COAT: Topcoat with Archco 65™ Acrylic Urethane, Archco 380™ Acrylic Epoxy or Archco 390™ Polysiloxane or Archco 381™ High-Gloss Hybrid. Store in a dry, well-ventilated area between 40°F and 90°F (4°C to 32°C) in original, unopened containers. Shelf life is at least 12 months under these conditions. It is recommended that all components be stored between 68°F to 86°F (20°C to 30°C) for 24 hours prior to use for optimum pumping and productivity.

Storage

Minimum 2 Years when @ 40°F (4°C) to 105°F (41°C).

Cleaning

Archco 400E™ Thinner, MEK or equivalent solvent cleaner.

Health & Safety

Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. Do not ingest. See Safety Data Sheet (SDS) for further information.

Packaging

Standard kit - 4-gallon (15 liter) kits.

Archco 300™ Epoxy Primer

TECHNICAL DATA

PROPERTIES	VALUE	LT HARDENER ADDED
Solids By Weight	85%	70%
Solids By Volume	76%	54%
Viscosity @ 77°F (25°C)	140 KU	140 KU
Pot Life	4 Hours	1 Hour
Theoretical Coverage	1219 ft ² /gal @ 1 mil dft (7.9 m ² /l @ 127 micron dft)	
Recommended D.F.T.	4.0 - 8.0 mils/coat (102 - 203 microns)	
Shelf Life @ 40°F (4°C) to 105°F (41°C)	2 years	2 years
Flash Point	40°F (4°C)	40°F (4°C)
Dry Time @ 77°F (25°C), 55% R.H. @35°F		
To Touch:	1 Hour	24 Hours
Tack Free:	3 Hours	48 Hours
To Recoat:	6 Hours	10 Hours min.
Recoat Window	90 days @ 77°F (25°C)	90 days @ 77°F (25°C)
Temperature Resistance (Dry)	200°F (93°C)	200°F (93°C)
V.O.C.	1.66 lbs/gal (199 grams/L)	1.50 lbs/gal (180 grams/L)
Thinning	Thinner 400 (5% -15%)	Thinner 400 (5% -15%)
Ratio by volume (A to B)	3:1 Ratio	3:1 Ratio
WT. / Gallon	12.25 lbs / gal	12.25 lbs / gal
Application Method	Brush, Roll, Spray	Spray Only
Application Equipment		
Conventional	DeVilbiss 510 Gun / E Tip + Needle, 704 Air Cap	
Airless	or Graco Pump, .012 - .021 Tip or equivalent	
Gloss	Semi-Gloss	
Color	Brick Red, Beige & Other Colors Upon Request.	



DENSO NORTH AMERICA

HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

info@densona.com

**A Member of Winn
& Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.