

ARCHCO™ 403D

Vinyl Ester Glass Flake Coating

Description

Archco 403D is a vinyl ester two-part high solids reinforced glass flake coating that offers outstanding resistance to corrosion and abrasion. It is resistant to corrosive acids, alkalis, salts and a range of oxidizing chemicals.

Uses

Corrosion protection for oil storage tank linings, filtration vessels, ion exchange vessels, effluent streams and water treatment facilities. Also, used for the protection of process vessels, stacks, ducts, fume scrubbers, fan cases and many other corrosive environments.

Features

- Excellent corrosion resistance
- Fast dry and set times
- High temperature tolerance
- High abrasion resistance
- Excellent undercutting resistance
- Very low water permeability
- Excellent water/sea water resistance
- Excellent undercutting resistance
- Excellent cathodic disbondment results
- High build up to 20 mils (508 microns) in one coat

Application

Prepare surfaces by grit blasting to a clean near white finish, SSPC-SP10/NACE No. 2. For larger areas the Archco 400D Primer shall be used.

To spray Archco 403D an air assist airless unit shall be used. The spray equipment shall have at an minimum Graco NXT Xtreme 50:1 ratio resin pump with a super slave catalyst pump adjustable from 1% to 3.5%, Centry Air Assist Spray Gun with tungsten carbide needle, pressure gauges, relief valve, flow meter, 2-1/2 gallon (9.5 L) catalyst supply bottle, 7-1/2 gallon (28.5 L) hopper for Part A, catalyst hose, resin hose, regulator, atomizing regulator and manifold. Consult with Denso for recommended supplier of equipment.

Initially mix Part A just prior to pouring Part A into hopper. Adjust catalyst pump from 1% to 3% depending on ambient temperatures. Note: Use of less than 1% catalyst will not produce a full cure of the coating material. Plate edges, corners and weld areas shall be stripe coated by brush prior to application of the first coat to help ensure adequate mil thickness in these areas. The coating shall be sprayed applied in two coats, each being 17 to 20 mils (432 - 508 microns) thick. A wet film thickness gauge should be used to measure uniform application of each coat. Clean tools and equipment with Acetone.

The dry film thickness of the completed coating shall be measured with an electronic instrument to ensure proper thickness. The finished cured coating shall be tested for holidays using a D.C. spark detector using 100 volts/mil (3937 V/mm).



Archco™ 403D

TECHNICAL DATA

PROPERTIES	VALUE
Solids Content	98 - 99%
Specific Gravity	1.2
Maximum Humidity During Application	90% RH
Operating Temperature	-4°F to 212°F (-20°C to 100°C)
Min. Substrate Temperature	50°F (10°C)
Minimum Dewpoint/Substrate Differential	Dewpoint +5°F (+3°C)
Dry Film Thickness Per Coat	17 - 20 mils (432 - 508 microns)
Theoretical Coverage	39 SF/Gal @ 40 mils (1016 microns) DFT
Overcoating Times 68°F (20°C)	Min. 6 hrs – Max. 3 days
Preferred Equipment	Consult with Denso
Pot life 73°F (23°C)	30 - 40 minutes
Typical Curing Characteristics	
Substrate Temperature 59°F (15°C)	Touch Dry – approx. 3.5 hrs Full Cure - 2-7 days
Shelf Life	4 - 6 months
Flash Point	88°F (31°C)
Abrasion Resistance ASTM D 4060	0.035gm
Adhesion Properties ASTM D 952	8 Mpa
Salt Water Resistance ASTM B 1117-57T	20,000 hrs – No effect
Cathodic Disbondment CSA Z245.02 Clause 12.6	
140°F (60°C) – 28 days	10 mm
Tensile Strength ASTM D 638	3975 psi (27.4 MPa)
Flexural Strength ASTM D 790	9425 psi (65 MPa)
Water Soak Adhesion CSA Z245.02 Clause 12.8	
140°F (60°C) – 28 days	Rating 2
Standard Atlas Test NACE TM0174	
140°F (60°C) – 28 days	Very good adhesion – no blisters
Pressurized Atlas Cell NACE TM0174	
140°F (60°C) – 28 days	Very good adhesion – no blisters
Autoclave	
212°F (100°C) – 168 hrs	Good adhesion – no blisters
257°F (125°C) – 168 hrs	Good adhesion – no blisters
Electrochemical Impedance Spectroscopy (EIS)	
140°F (60°C) – 28 days, untested	Log Z = 9.1 ohms/cm _≤
140°F (60°C) – 28 days, Pressurized Atlas Cell	Log Z = 9.0 ohms/cm _≤
VOC	2.75 lbs/gal (1.25 kg/L) (Includes Styrene)

STORAGE: Minimum 4 - 6 months when stored in original containers @ 41°F (5°C) to 80°F (27°C).

CLEANING: Clean equipment with MEK or equivalent solvent cleaner.

HEALTH AND SAFETY: Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheet for further information.

PACKAGING: 1 gallon (3.7 L) kit and 5 gallon (19 L) kits standard. Other kit sizes are available.



DENSO NORTH AMERICA

HOUSTON:

9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:

90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International™

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.