

ViscOTAQTM COATING PATCH

Visco-Elastic Repair Patch

Description

Viscotaq Coating Patch is a visco-elastic repair patch for underground and aboveground substrates. It is provided as a 3.5" x 3.5" patch compound with a solvent wipe and sandpaper included for surface preparation.

Uses

- Cadwelds
- Pin braze connections
- Holiday repairs

Features

- Impermeable to moisture and gases
- Immediate adhesion to substrate / permanent wetting characteristics
- No primer needed
- Easy to apply, no mixing or messy clean-up
- Minimal surface preparation required (sandpaper / solvent wipe)
- Self-healing characteristics
- Inert material, no deterioration over time
- Resistant to aggressive soil conditions such as water, acid, salts, or soil organics
- Ready for immediate service
- Contains no solvents, no carcinogens, non-toxic, non-flammable
- Never cracks or becomes brittle
- Flexible, pliable, easily conforms to irregular shapes
- UV resistant
- Freeze / thaw resistant
- Application ranges from -45°F to 158°F (-45°C to 70°C)
- Ability to fill voids and anomalies of substrate

Surface Prep

- Minimum surface preparation should be to roughen surface of sufficient area around damage to exceed patch area with sandpaper provided.
- Once loose materials are removed, clean surface with solvent wipe provided to remove any remaining dust, grease, and moisture.
- Surface of substrate should be 5°F (3°C) or greater above the dew point.



TECHNICAL DATA SHEET

- Surface inspected prior to application with any defects documented.
- Always keep the working area clean and dry. Avoid the presence of water. Any adjacent coating should be roughened by means of sandpaper.

Application

- Remove the release liner and place the adhesive side onto the substrate.
- Apply pressure over entire patch area to ensure good contact with surface.
- For coating repairs in difficult to reach areas, the Velcro disk attached to the patch can be used to attach to a placement tool configured appropriately to reach the repair area.

Storage

When stored in original unopened packaging at 40°F to 140°F (4°C to 60°C), Viscotaq Coating Patch has a recommended storage period of 5 years from date of manufacture. Material exceeding this period may be inspected and recertified for continued use.. Due to the adhesive nature of the product, release films / papers should be kept in place during storage and whenever the material is placed on its side after removal from the case.

Packaging

A single Viscotaq Coating Patch contains one each 3.5" x 3.5" repair patch, one each solvent wipe packet, and one each square of 80 grit sandpaper.

A case of coating patches contains 48 each kits as described above.

TECHNICAL DATA SHEET

Tech Data

Properties	Imperial	Metric
Material State	Semisolid	<i>Semisolid</i>
Thickness (ISO 4593:1993E)	>0.375 in.	>9.5 mm
Density (DIN 53479)	1.1-1.3	1.1-1.3
Glass Transition Temperature (ASTM E1356)	-45.26°F	42.92°C
Water Vapor Permeability (ASTM E96/96M)	$<5.6 \times 10^{-4}$ lb/day/ft ² /psi	$<4 \times 10^{-4}$ g/day/m ² /Pa
Water Absorption (ISO 62)	<0.03%	<0.03%
Volume Resistivity (ASTM D257)	$>8.7 \times 10^{12}$ ohm*in	$>2.2 \times 10^{13}$ ohm*cm
Surface Resistivity (ASTM D257)	$>6.0 \times 10^{16}$ ohm*ft ²	$>5.6 \times 10^{15}$ ohm*m ²
Application Range	-45°F to 158°F	-45°C to 70°C
Dielectric Strength (ASTM D149)	>445 KV/in	>17.5 kV/mm
Impact Strength (ISO 21809-3 Annex D)	>133 in-lb _i	>15 J (Immediate)
Indentation (ISO 21809-3 Annex E)	No holidays	No holidays
UV/Weather Cycle Test (ASTM D4587, 1000 Hours)	Excellent, rating 10	Excellent, rating 10
Wet Adhesion Test (CSA Z245-20 Sec. 12.14)	Excellent	Excellent
Chemical Resistance in Aggressive Soils Tested in Sulfuric Acid (30%), Nitric Acid (10%), Phosphoric Acid (20%), Hydrochloric Acid (10%)	Excellent	Excellent
	No deterioration, 72 hours at 158°F / No corrosion, 72 hours at 158°F	No deterioration, 72 hours at 70°C / No corrosion, 72 hours at 70°C



DENSO, INC.

HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

info@densona.com

**A Member of Winn
& Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.